

IN THE SPECIFICATION:

Please replace the paragraph beginning at page 47, line 1, with the following rewritten paragraph:

After pre-drying for 3 hours at 70°C to [[770°C]] 75°C, the product was additionally dried under reduced pressure for 1 hour at 180°C to prepare highly liquid absorbent resin particles (H).